



## PROXXON DS 460 - EXTENSION SPRING 27094-04

### Liquid glazes

These Glazes are used on mature bisque.

The recommended firing temperature is 960C-980C.

Glazes can be intermixed to obtain new colors, except for colors red and yellow (#12889-#12907) that are cadmium-selenium colors and can only be intermixed with each other to create orange.

Can be applied with brush or sponge.

If thinning is necessary, add a small amount of water and mix well.

SKU 12884