



SLIP CASTING MOLDS PLASTER

This highly absorbent gypsum is suitable for making ceramic slip casting molds.

Technical features:

- Gypsum / water ratio: 1.49 / 1.61: 1
- Porosity: 44%
- % expansion after two hours: 0.24
- Hardness: 26 MN / m²
- Vicat ring: 17-22 cm

SPECIFICHE

SKU	Packaging
48699	5 KG
17922	40 KG