



1060°C



1140°C



1250°C

WHITE STONEWARE CLAY K123

White stoneware clay body ideal for Raku technique. **Key**

Features

- Temperature range 1000 - 1280 ° C
- Color after firing: ivory (varies according to the temperature used)
- 25% chamotte, 0 - 0.5 mm
- 5% drying shrinkage, to be added to firing shrinkage (4.5% at a temperature of 1200 ° C)
- In 10 kg packages

Color / Size

10 kg

White

53660