



FLÜSSIGE GLASUR HSC SERIEN

Liquid glazes

These Glazes are used on mature bisque.

The recommended firing temperature is 950C-980C.

Glazes can be intermixed to obtain new colors, except for colors red and yellow (#12889-#12907) that are cadmium-selenium colors and can only be intermixed with each other to create orange.

Can be applied with brush or sponge.

If thinning is necessary, add a small amount of water and mix well.

Farbe / Größe

	3800 ML	118 ML	473 ML	19000 ML
Weisse	2290422906			
Arctic White	22863	12892	15956	22907
Panama Beige	22898	21194	22847	
Zitronengelb	22889	12903	22839	
Intensives Gelb	22897	12907	15958	
Magenta	22872	12896	22822	
Violett	22874	21181	22824	
Blau Violett	22858	21175	22812	
Pretty Turquoise	22866	21177	22817	
Frog	22864	21176	22815	
Weihnachtsgrün	22865	12893	22816	
Schwarz	22860	12890	15959	
Matt-Weisse	22861	22807	22813	
Marfil Opaco	59342	59334	59338	
Mattes Orange	37414	37412	37413	
Karotte Orange Matt	59343	59335	59339	
Seidenrot	22902	21198		
Rot Satin			22851	
Azul opaco	59344	59336	59340	
Verde opaco	59345	59337	59341	
Mattschwarz	22886	22808	22836	

Farbe / Größe	3800 ML	118 ML	473 ML	19000 ML
Pearly Cream	22877	21182	22827	
Flecked Yellow	22878	21183	22828	
Salbei Grün	22884	21187	22834	
Jadegrün	22869	21179	22819	
Persisch Blau	22890	21190	22840	
Jeans	22888	21189	22838	
Coffee Mousse	22885	21188	22835	
Leder	22882	21185	22832	
Siena Erde	22881	12901	22831	
Metallisches Kupfer	22880	12900	22830	
Oxidated Silver	22887	12902	22837	
Silbermetallic	22873	12897	22823	